Leading or Trailing Strokes

Posted by wickededge - 21 Aug 2012 16:45

I did a quick experiment with the .6 Micro-Fine Ceramic stones and edge-leading and edge-trailing sharpening. First I polished the edge .25um with the kangaroo strops. Here is the clean edge:

I didn't go for perfect, just good enough to have a clean slate.

Next I did 5 very light trailing strokes with the .6um Micro-Fines at 5 degrees wider. Here is the result:

I did another 20 strokes, edge-trailing:

==========

Re: Leading or Trailing Strokes

Posted by RalphHoneycutt - 22 Aug 2012 10:07

Clay, What angle did you use to clean up the edge with the 'roo and then what angle did you use with the 0.6um micro-fine ceramics?

Thanks,

Ralph

==========

Re: Leading or Trailing Strokes

Posted by razoredgeknives - 22 Aug 2012 10:34

---

wickededge wrote:

cbwx34 wrote:

wickededge wrote:

Clearly a big burr (you know, about 4 microns or something) was formed.

Haha... I do forget the magnification we're looking at these sometimes...

I'm looking at them this a.m. on a big screen tv. (god bless modern technology).

Now I'm wondering if it's possible, to take a shot of the edge looking straight down... to see if that shows any differences between the edge trailing vs. edge leading edges?

I've been waiting for this for a while! Thanks so much Clay! Can'twait to see different results

Funny you should mention that - I was just working on it this morning and modified my jig to allow the blade to sit up vertically under the scope. It's hard to find the edge but once I do, I can focus on it fairly well. I did some measurements and got and edge thickness of between .45um and .29um with the Mirco-Fine .6 stones at 28 degrees.

==========

Re: Leading or Trailing Strokes

Posted by cbwx34 - 22 Aug 2012 10:34

---

wickededge wrote:

Funny you should mention that - I was just working on it this morning and modified my jig to allow the blade to sit up vertically under the scope. It's hard to find the edge but once I do, I can focus on it fairly well. I did some measurements and got and edge thickness of between .45um and .29um with the Mirco-Fine .6 stones at 28 degrees.

Cool. These would be interesting to see as well.

It might be worth mentioning... this may be old news to those who have been involved in sharpening for a while, but if you're new you might not know this... that there is some debate over which method leaves a better edge, trailing or leading. There is differences in the type of burr formed, how the burr is removed and the edge it leaves, whether or not edge leading "smashes" the edge into the abrasive particles preventing it from ever getting sharp, and other factors. Many sharpeners base their whole method on these ideas, and while most seem to make common sense (on either side of the issue), little has been done to actually prove or disprove the "facts". So, while it's hard to draw conclusions from just a few photos, over time, this could prove to be very beneficial.

==========

Re: Leading or Trailing Strokes

Posted by wickededge - 22 Aug 2012 10:37

Hey Ralph,

I have the sharpener set at 25 degrees for the .6um and 30 for the for the roo strops.

RalphHoneycutt wrote:

Clay, What angle did you use to clean up the edge with the 'roo and then what angle did you use with the 0.6um micro-fine ceramics?

Thanks,

Ralph

==========

Re: Leading or Trailing Strokes

Posted by RalphHoneycutt - 22 Aug 2012 10:56

Clay, For some reason I was expecting the opposite. With the roo strops at 30 deg, would it not roll the edge over? ... and with the 0.6um at 25 deg, I would have expected it to cut somewhere on the shoulder and not the edge. I think I am missing something.

Thanks,

Ralph

==========

Re: Leading or Trailing Strokes

Posted by wickededge - 22 Aug 2012 11:27

_____

Ralph, you're right I just goofed up my answer. I stropped with the roo at 25 and used the .6 ceramics at 30! Thanks for catching it.

RalphHoneycutt wrote:

Clay, For some reason I was expecting the opposite. With the roo strops at 30 deg, would it not roll the edge over? ... and with the 0.6um at 25 deg, I would have expected it to cut somewhere on the shoulder and not the edge. I think I am missing something.

Thanks,

Ralph

==========